

P/N: LV-AL (Low Viscosity)

FASTELFOIL PA250-LV Product Description


FastelFoil PA250-LV is a heat sealable aluminum foil designed for direct heat sealing or induction sealing to many types of plastic surfaces. The PA250-LV seal composition is a polyethylene based heat activated seal coating exhibiting low viscosity at its melt point allowing for increased flow and surface wetting properties when compared to the PA250-HV (high viscosity) version. PA250-LV provides flow and conformability to uneven or unique surfaces. Due to its inert polyethylene base, FastelFoil PA250-LV an ideal candidate for medical device diagnostic applications and sensitive electronic applications needing an easy bonding process and seal barrier especially when not dealing with ultra-flat surfaces. FastelFoil PA250-LV can be delivered in custom defined rolls, die cut individuals, die cut sheet arrays or die cut continuous reel formats.

Product Features
Excellent Sealing Characteristics
Puncture or Peel Foil Configurations
Uniform Bond Line Thickness
Controllable Flow Upon Heating
Quick Curing / No Set Heating Time

Popular Sealing Surfaces
Polycarbonate
Polyethylene
Polypropylene
ABS / Styrene / Vinyl

FastelFoil PA250-LV Construction / Format

Seal Base Coating:	Polyethylene Blend
Seal Thickness:	1 Mil, 2 Mil, 3 Mil, 5 Mil Custom thickness available
Seal Color:	Clear
Aluminum Thickness:	0.5 Mil, 1 Mil, 1.5 mil, 2 mil Custom thickness available
Delivery Formats:	Master or Slit Rolls / Die Cuts
Lamination Options:	PET Film, C1S Paper Backing Lamination
Printing Options:	2 Color, Flexographic, Repeat, Registration Direct to foil or top side laminate
Fastel Rolls or Die Cuts:	Customer defined roll width Individual die cut pieces Multiple die cuts per card Continuous die cut rolls



Processing Note: standard roll material contains a release liner on PE seal coating side and can be collected up during roll unwind. Roll material is available with no release liner (self-wound) but should be stored at room temperature 78F/25C to aid in preventing very light tackiness of material during unwind.

FastelFoil PA250-LV General Direct Heat Press Sealing Recommendations

Seal Coating Minimum Melt Point:	250F / 120C minimum
Max Continuous Operating Temp (post sealing):	215F / 102C
Viscosity Reference:	1,650 CPS @ 300F/150C
Full Bond / Sealing Temperature:	265F – 330F (130C to 165C) (see note 1) 10 - 50 PSI+ 3 to 60 seconds+ (dependent on time and pressure)

Typical Heating Devices: Heat Press, Induction Seal, Curing Oven, Heated Rollers

Note 1: listed are general direct heat sealing parameters only. The above should be used as a general guideline and basis of expanded customer DOE (design of experiment) testing within the scope of their equipment, flatness conditions, chamber geometry and application requirements. Due to flow capability of heat seal coating, factors such as time, temperature and pressure conditions should be tested to yield desired flow objectives.

Samples or More Information: For more information or to receive samples for testing, please contact us toll free at 1-888-989-3832 (US Only) +1-949-369-7676 (international) or e-mail info@fasteladhesives.com

Fastel Adhesives
208 Avenida Fabricante
San Clemente, CA 92672, USA
www.fasteladhesives.com

Fastel Adhesives * 208 Avenida Fabricante * San Clemente, CA 92672, USA

The information contained herein is to the best of our knowledge and belief to be accurate. Physical properties shown above are typical values and are not intended for use in writing specifications. However, since the conditions of handling and of use are beyond our control, we make no guarantee of results and assume no liability for damages incurred by following these suggestions. Nothing contained herein is to be construed as a recommendation for use in violation of any patents or of applicable laws or regulations. REV 2020